

PAPEL FLUTING HP

Papel 100% reciclado
CODE CEPI: 42

CARACTERÍSTICAS TÍPICAS

	115	120	130	140	150	160	170	
SCT, DT ISO 9895	2,35	2,52	2,86	3,04	3,28	3,50	3,74	KN.m
CMT30, DM UNE-EN ISO7263	239	262	289	341	366	397	419	N
CCT30, DT Norma correspondiente	1,86	1,99	2,25	2,47	2,62	2,79	2,82	KN.m
POROSIDAD Gurley UNE 57066	55	55	55	55	55	55	55	seg.

CARACTERÍSTICAS GARANTIZADAS

	115	120	130	140	150	160	170	
SCT, DT ISO 9895	2,19	2,29	2,60	2,80	3,00	3,20	3,40	KN.m
CMT30, DM UNE-EN ISO7263	218	227	255	302	322	356	378	N
CCT30, DT Norma correspondiente	1,73	1,78	2,06	2,21	2,32	2,48	2,64	KN.m
POROSIDAD Gurley UNE 57066	45	45	45	45	45	45	45	seg.

Humedad: 8,5% ±1

Gramaje: nominal ±3%

Revisión: Enero 2020

