

PAPEL FLUTING HP

Papel 100% reciclado
CODE CEPI: 44

CARACTERÍSTICAS TÍPICAS

| | 115 | 120 | 130 | 140 | 150 | 160 | 170 | |
|------------------------------------|------|------|------|------|------|------|------|------|
| SCT, DT ISO 9895 | 2,35 | 2,52 | 2,86 | 3,04 | 3,28 | 3,50 | 3,74 | KN.m |
| CMT30, DM UNE-EN ISO7263 | 239 | 262 | 289 | 341 | 366 | 397 | 419 | N |
| CCT30, DT Norma correspondiente | 1,86 | 1,99 | 2,25 | 2,47 | 2,62 | 2,79 | 2,82 | KN.m |
| POROSIDAD Gurley UNE 57066 | 55 | 55 | 55 | 55 | 55 | 55 | 55 | seg. |

CARACTERÍSTICAS GARANTIZADAS

| | 115 | 120 | 130 | 140 | 150 | 160 | 170 | |
|------------------------------------|------|------|------|------|------|------|------|------|
| SCT, DT ISO 9895 | 2,19 | 2,29 | 2,60 | 2,80 | 3,00 | 3,20 | 3,40 | KN.m |
| CMT30, DM UNE-EN ISO7263 | 218 | 227 | 255 | 302 | 322 | 356 | 378 | N |
| CCT30, DT Norma correspondiente | 1,73 | 1,78 | 2,06 | 2,21 | 2,32 | 2,48 | 2,64 | KN.m |
| POROSIDAD Gurley UNE 57066 | 45 | 45 | 45 | 45 | 45 | 45 | 45 | seg. |

Humedad: 8,5% ±1

Gramaje: nominal ±3%

Revisión: Enero 2021



Intertek



La marca de la
gestión forestal
responsable

