

PAPEL FLUTING

Papel 100% reciclado
CODE CEPI: 41

CARACTERÍSTICAS TÍPICAS

	90	95	100	105	110	115	
SCT, DT ISO 9895	1,44	1,52	1,70	1,78	1,87	1,96	KN.m
CMT30, DM UNE-EN ISO7263	144	152	160	169	177	186	N
CCT30, DT UNE-EN ISO16945	1,10	1,15	1,20	1,25	1,30	1,35	KN.m
POROSIDAD Gurley UNE 57066	45,0	45,0	45,0	45,0	45,0	45,0	seg.

CARACTERÍSTICAS GARANTIZADAS

	90	95	100	105	110	115	
SCT, DT ISO 9895	1,30	1,37	1,53	1,61	1,68	1,76	KN.m
CMT30, DM UNE-EN ISO7263	126	133	140	148	155	162	N
CCT30, DT UNE-EN ISO16945	0,94	0,99	1,05	1,10	1,15	1,20	KN.m
POROSIDAD Gurley UNE 57066	35,0	35,0	35,0	35,0	35,0	35,0	seg.

Humedad 8% ±1

Gramaje: nominal ±3%

Revisión: Enero 2021

