

# PAPEL TESTLINER

Papel 100% reciclado  
CODE CEPI: 30

## CARACTERÍSTICAS TÍPICAS

	130	140	150	160	170	
SCT, DT ISO 9895	2,08	2,31	2,47	2,63	2,89	KN.m
I.MULLEN UNE 57058	2,30	2,35	2,35	2,35	2,40	KPa.m <sup>2</sup> /gr
POROSIDAD Gurley UNE 57066	45,0	45,0	45,0	45,0	45,0	Seg.
COBB60" ISO 535	30,0	30,0	30,0	30,0	30,0	Gr.

## CARACTERÍSTICAS GARANTIZADAS

	130	140	150	160	170	
SCT, DT ISO 9895	1,87	2,08	2,22	2,37	2,60	KN.m
I.MULLEN UNE 57058	2,07	2,12	2,12	2,12	2,16	KPa.m <sup>2</sup> /gr
POROSIDAD Gurley UNE 57066	35,0	35,0	35,0	35,0	35,0	Seg.
COBB60" ISO 535	50,0	50,0	50,0	50,0	50,0	Gr.

Humedad 7,5 ±1

Gramaje nominal ±3%

Revisión: Enero 2022

