

PAPEL BICOLOR

Papel 100% reciclado
CODE CEPI: 38

CARACTERÍSTICAS TÍPICAS

	100	105	110	115	120	125	
SCT, DT ISO 9895	1,50	1,57	1,64	1,72	1,80	1,88	KN.m
I.MULLEN UNE 57058	2,10	2,10	2,10	2,10	2,10	2,10	KPa.m ² /gr
POROSIDAD Gurley UNE 57066	35,0	35,0	35,0	35,0	35,0	35,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

CARACTERÍSTICAS GARANTIZADAS

	100	105	110	115	120	125	
SCT, DT ISO 9895	1,35	1,42	1,49	1,55	1,62	1,69	KN.m
I.MULLEN UNE 57058	1,90	1,90	1,90	1,90	1,90	1,90	KPa.m ² /gr
POROSIDAD Gurley UNE 57066	32,0	32,0	32,0	32,0	32,0	32,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

Humedad 7,5% ±1

Gramaje: nominal ±3%

Revisión: Enero 2023

