

PAPEL BICOLOR

Papel 100% reciclado
CODE CEPI: 38

CARACTERÍSTICAS TÍPICAS

	100	105	110	115	120	125	
SCT, DT ISO 9895	1,50	1,57	1,64	1,72	1,80	1,88	KN.m
I.MULLEN ISO 2758	210	221	231	242	252	263	Kpa
POROSIDAD Gurley ISO 5636-5	35,0	35,0	35,0	35,0	35,0	35,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

CARACTERÍSTICAS GARANTIZADAS

	100	105	110	115	120	125	
SCT, DT ISO 9895	1,35	1,42	1,49	1,55	1,62	1,69	KN.m
I.MULLEN ISO 2758	190	200	209	219	228	238	Kpa
POROSIDAD Gurley ISO 5636-5	32,0	32,0	32,0	32,0	32,0	32,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

Humedad 7,5% ±1

Gramaje: nominal ±3%

Revisión: Enero 2023



La marca de la
gestión forestal
responsable

