

# PAPEL DUAL USE (TL-2)

Papel 100% reciclado  
CODE CEPI: 52

## CARACTERÍSTICAS TÍPICAS

	110	115	120	125	130	135	
SCT, DT ISO 9895	1,92	2,02	2,12	2,20	2,28	2,37	KN.m
CMT30, DM UNE-EN ISO7263	173	180	188	196	204	212	N
I.MULLEN ISO 2758	242	253	264	275	286	307	Kpa
COBB60" ISO 535	30	30	30	30	30	30	Gr/m2

## CARACTERÍSTICAS GARANTIZADAS

	110	115	120	125	130	135	
SCT, DT ISO 9895	1,76	1,85	1,95	2,02	2,10	2,18	KN.m
CMT30, DM UNE-EN ISO7263	163	171	179	185	191	197	N
I.MULLEN ISO 2758	223	233	243	253	263	283	Kpa
COBB60" ISO 535	50	50	50	50	50	50	Gr/m2

Humedad: 8% ±1

Gramaje: nominal ±3%

Revisión: Enero 2023



Intertek



La marca de la  
gestión forestal  
responsable



# PAPEL DUAL USE (TL-2)

Papel 100% reciclado  
CODE CEPI: 52

## CARACTERÍSTICAS TÍPICAS

	140	150	160	170	180	190	200	
SCT, DT ISO 9895	2,46	2,64	2,81	2,99	3,14	3,26	3,38	KN.m
CMT30, DM UNE-EN ISO7263	220	236	251	267	280	294	309	N
I.MULLEN ISO 2758	329	353	376	400	420	441	453	Kpa
COBB60" ISO 535	30	30	30	30	30	30	30	Gr/m2

## CARACTERÍSTICAS GARANTIZADAS

	140	150	160	170	180	190	200	
SCT, DT ISO 9895	2,26	2,43	2,59	2,75	2,88	2,99	3,10	KN.m
CMT30, DM UNE-EN ISO7263	203	217	226	238	245	252	259	N
I.MULLEN ISO 2758	303	324	346	368	382	396	408	Kpa
COBB60" ISO 535	50	50	50	50	50	50	50	Gr/m2

Humedad: 8% ±1

Gramaje: nominal ±3%

Revisión: Enero 2023

