

PAPEL BICOLOR

Papel 100% reciclado
CODE CEPI: 38

CARACTERÍSTICAS TÍPICAS

	100	105	110	115	120	125	
SCT, DT ISO 9895	1,50	1,57	1,64	1,72	1,80	1,88	KN.m
I.MULLEN ISO 2758	210	221	231	242	252	263	Kpa
POROSIDAD Gurley ISO 5636-5	35,0	35,0	35,0	35,0	35,0	35,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

CARACTERÍSTICAS GARANTIZADAS

	100	105	110	115	120	125	
SCT, DT ISO 9895	1,35	1,42	1,49	1,55	1,62	1,69	KN.m
I.MULLEN ISO 2758	190	200	209	219	228	238	Kpa
POROSIDAD Gurley ISO 5636-5	32,0	32,0	32,0	32,0	32,0	32,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

Humedad 7,5% ±1

Gramaje: nominal ±3%

Revisión: Enero 2024



La marca de la
gestión forestal
responsable



PAPEL BICOLOR

Papel 100% reciclado
CODE CEPI: 38

CARACTERÍSTICAS TÍPICAS

	130	140	150	160	170	180	
SCT, DT ISO 9895	1,94	2,09	2,25	2,39	2,54	2,69	KN.m
I.MULLEN ISO 2758	273	294	315	336	357	378	Kpa
POROSIDAD Gurley ISO 5636-5	35,0	35,0	35,0	35,0	35,0	35,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

CARACTERÍSTICAS GARANTIZADAS

	130	140	150	160	170	180	
SCT, DT ISO 9895	1,76	1,89	2,03	2,16	2,30	2,44	KN.m
I.MULLEN ISO 2758	247	266	285	304	323	342	Kpa
POROSIDAD Gurley ISO 5636-5	32,0	32,0	32,0	32,0	32,0	32,0	Seg.
COBB60" ISO 535	0,0	0,0	0,0	0,0	0,0	0,0	Gr.

Humedad 7,5% ±1

Gramaje: nominal ±3%

Revisión: Enero 2024



La marca de la
gestión forestal
responsable

