

PAPEL DUAL USE (TL-2)

Papel 100% reciclado
CODE CEPI: 52

CARACTERÍSTICAS OBJETIVO

	110	115	120	125	130	135	
SCT, DT ISO 9895	1,92	2,02	2,12	2,20	2,28	2,37	KN.m
CMT30, DM UNE-EN ISO7263	173	180	188	196	204	212	N
MULLEN ISO 2758	242	253	264	275	286	307	Kpa
COBB60" ISO 535	30	30	30	30	30	30	Gr/m2

CARACTERÍSTICAS GARANTIZADAS

	110	115	120	125	130	135	
SCT, DT ISO 9895	1,76	1,85	1,95	2,02	2,10	2,18	KN.m
CMT30, DM UNE-EN ISO7263	163	171	179	185	191	197	N
MULLEN ISO 2758	223	233	243	253	263	283	Kpa
COBB60" ISO 535	50	50	50	50	50	50	Gr/m2

Humedad: 8% ±1

Gramaje: nominal ±3%

Revisión: Enero 2026



La marca de la
gestión forestal
responsable



PAPEL DUAL USE (TL-2)

Papel 100% reciclado
CODE CEPI: 52

CARACTERÍSTICAS OBJETIVO

	140	150	160	170	180	190	200	
SCT, DT ISO 9895	2,38	2,55	2,72	2,89	3,06	3,23	3,40	KN.m
CMT30, DM UNE-EN ISO7263	224	240	256	272	288	304	320	N
MULLEN ISO 2758	308	330	352	374	396	418	440	Kpa
COBB60" ISO 535	30	30	30	30	30	30	30	Gr/m2

CARACTERÍSTICAS GARANTIZADAS

	140	150	160	170	180	190	200	
SCT, DT ISO 9895	2,24	2,40	2,56	2,72	2,88	3,04	3,20	KN.m
CMT30, DM UNE-EN ISO7263	196	210	224	238	245	259	272	N
MULLEN ISO 2758	280	300	320	340	360	380	400	Kpa
COBB60" ISO 535	50	50	50	50	50	50	50	Gr/m2

Humedad: 8% ±1

Gramaje: nominal ±3%

Revisión: Enero 2026



La marca de la
gestión forestal
responsable

